

## **SPARFILL 82**

### **PRODUCT INFORMATION**

**SPARFILL 82** is a high alumina ,dustless, dry vibratable refractory. It is used for backup lining in bricked ladles, tundish, and precast shapes.

#### **PHYSICAL PROPERTIES**

Maximum Service Temperature	3200 F
Bulk Density	188-192 lbs./cu.ft.

#### **TYPICAL CHEMICAL ANALYSIS, %**

Al <sub>2</sub> O <sub>3</sub>	82.50
SiO <sub>2</sub>	10.00
Fe <sub>2</sub> O <sub>3</sub>	1.20
TiO <sub>2</sub>	3.40
B <sub>2</sub> O <sub>3</sub>	2.00
MgO	0.30
CaO	0.30
Alkalies	0.30

The above are average results and do not constitute a specification.

**SPARFILL 82** is available packaged in 50/ 60# bags, 30 / 100# bags, or 3000# bulk bags – all palletized and shrink-wrapped.