

SPARLITE 10.5.1.4

SPARLITE 10.5.1.4 is an intermediate strength Portland cement based Haydite-Vermiculite gunning mix designed for fireproofing applications.

PHYSICAL PROPERTIES

Material Density (lb/ft ³)	75-95
Compressive Strength (psi)	1000 - 2000
Thermal Conductivity (BTU in °F-hr-ft ² @ 75°F mean temperature.)	≈ 3
Hardness (Shore D)	70-90
Fire Time Rating @ 3 hours (Thickness in Inches)	2"

The above are average results and do not constitute a specification.

SPARLITE 10.5.1.4 is available in 50 – 50# bags/pallet, or in various sized bulk bags, palletized and shrink-wrapped.

NOTE: MUST BE STORED IN A DRY PLACE.

Data shown are average results of standard ASTM tests unless otherwise noted. Results may vary subject to variations in manufacturing, testing, and installation procedures in the field.