

SPARLITE 90P LI

SPARLITE 90P LI is a 90 lb. low iron medium weight insulating refractory castable designed for pumpcast and/or shotcreting applications.

PHYSICAL PROPERTIES

Maximum Service Temperature	2600°F
Dry Castable Requirement	88 lbs./cu.ft.
Mixing Water Required (pumpable consistency)	25.0 to 26.0%
Bulk Density	
After Heating to 1500°F	88 – 92 lbs/cu.ft.
Cold Crushing Strength	
After Heating to 1500°F	900 – 1200 psi
After Heating to 2000°F	800 – 1100 psi
Linear Change, %	
After Heating to 1500°F	-0.0 to -0.3
After Heating to 2000°F	-0.1 to -0.4
Thermal Conductivity	
<u>Mean Temp</u>	<u>BTU/ft²/ F/in</u>
500°F	2.4
1000°F	2.5
1500°F	2.85
Typical Chemical Analysis, %	
Al ₂ O ₃	44.3
SiO ₂	40.7
CaO	11.7
TiO ₂	1.4
Fe ₂ O ₃	1.0
MgO	0.2
Alkalies	0.6

The above are average results and do not constitute a specification.

SPARLITE 90P LI is available in 60# bags or 1000# bulk bags, palletized and shrink-wrapped.

NOTE: CASTABLES MUST BE STORED IN A DRY PLACE

Data shown are average results of standard ASTM tests unless otherwise noted. Results may vary subject to variations in manufacturing, testing, and installation procedures in the field.